


TECHNICAL DATA SHEET

Colour	
Composition	Graphite based wire mesh reinforced with polymer coating both sides
Density DIN 28090-2 (g/cm³)	0,9 - 1,1
Min/Max recommended Peak Temperature (°C)	-200/+450
Max operating pressure (bar)	150
Leakage DIN 3535-6 (mg*s ⁻¹ *m ⁻¹)	≤ 0,1
Creep relaxation DIN 3535-6 (%)	≤ 8
Compressibility DIN 3535-6 (%)	40 - 50
Recovery DIN 3535-6 (%)	3 - 7
Availability Sheets size (mm)	1.500x1.500 1.500X1.000
Thickness (mm)	0,5 to 3
Tolerances Sheets size (mm) Thickness (%)	+/- 50 +/- 10

Other sheet sizes and thicknesses available upon request.
Maximum temperature and pressure values cannot be used simultaneously.
Typical parameters of 1,5 mm thickness jointing.
For a detailed list of our approvals please visit the dedicated area on our website
www.fmi-spa.com/approvals

All technical data is based on laboratory tests.
FMI spa reserves the right to modify the characteristics of its entire product range without obligation to anyone.



Via Consolare, 41/43 - 25030 Zocco di Erbusco - (BS) ITALY
Tel. +39 030 7386033 - Fax +39 030 7386035
www.fmi-spa.com

P.IVA IT 02170220178