

TECHNICAL DATA SHEET

Colour	
Composition	Graphite laminate reinforced with a flat stainless steel multilayers core
Density DIN 28090-2 (g/cm ³)	1,3 - 1,6
Min/Max recommended Peak Temperature (°C)	-200/+550
Max operating pressure (bar)	300
Leakage DIN 3535-6 (mg*s ⁻¹ *m ⁻¹)	≤ 0,1
Creep relaxation DIN 3535-6 (%)	≤ 5
Compressibility DIN 3535-6 (%)	30 - 45
Recovery DIN 3535-6 (%)	3 - 7
Availability Sheets size (mm)	1,500x1,500 1,000x1,000 1,500x1,000
Thickness (mm)	1 to 6
Tolerances Sheets size (mm) Thickness (%)	+/- 50 +/- 10

Other sheet sizes and thicknesses available upon request.
Maximum temperature and pressure values cannot be used simultaneously.
Typical parameters of 1,5 mm thickness jointing.
For a detailed list of our approvals please visit the dedicated area on our website
www.fmi-spa.com/approvals

All technical data is based on laboratory tests.
FMI spa reserves the right to modify the characteristics of its entire product range without obligation to anyone.

